



KE2090 Thermoplastic Compatibility
Ran in LIMS Tech Center

Manufacturer	Type	Grade	Shore A	Process for Adhesion
Bayer Material Science	High Heat PC	Apec 1745	40	General Overmolding
Bayer Material Science	High Heat PC	Apec 2095	40	General Overmolding
Bayer Material Science	PC	Makrolon AL2647	40/50	General Overmolding
Bayer Material Science	PC	Makrolon 2608-000000	40/50	General Overmolding
Bayer Material Science	PC	Makrolon RX1805	40	General Overmolding
Bayer Material Science	PC	Makrolon 2458	40	General Overmolding
Bayer Material Science	PC	Makrolon RX2530	40	General Overmolding
Bayer Material Science	PC	Makrolon 2858	40	General Overmolding
Bayer Material Science	PC	Makrolon 2405	50	General Overmolding
Bayer Material Science	PC	Bayblend TP4065	50	General Overmolding
Sabic	PC	Lexan HPS2	40	Pre-Heat substrate
Sabic	PC	Lexan HP2NR	40	Pre-Heat substrate
Sabic	PBT	Valox HX215HP	40	General Overmolding
Sabic	PBT/PC	Valox V3900WX	40	Pre-Heat substrate
Sabic	30% GF PBT	Valox HX 420HP	50	General Overmolding
Solvay	PSU	Udel P1700	40	General Overmolding
Solvay	PPSU	Radel R-5000	40	Pre-Heat substrate

Updated May 2017