



KE-5560U

Product Description

Shin-Etsu KE-5560 U is a nominal 60 durometer phenyl (PVMQ) base.

Product Features

- This material was designed for its excellent vibration dampening characteristics. Because of its phenyl content, it also has excellent low temperature characteristics.

Typical Applications

- Electronic CD mounts.
- Motor and engine mounts.
- Military and aeronautical vibration dampening devices.

Typical Properties

Type of HCR	Low Temperature
Cure Agent	DBPH-50
Durometer	60
Tensile Strength (psi)	1100
Elongation (%)	470
Specific Gravity	1.45
Tear Die B (ppi)	125
Compression Set (%)	11
Comp. Set Time (hours)	22
Comp. Set Temp. (°C)	180
Comp. Set Temp. (°F)	356
Press Cure/Post Cure	Post
Post Cure Time (hours)	4
Post Cure Temp. (°C)	200
Post Cure Temp. (°F)	392

Note: Values are not for specification purposes.

Warranty- The information and data contained herein are believed to be accurate and reliable; however it is the user's responsibility to determine suitability of use. Since Shin-Etsu Silicones, Inc. cannot know all of the uses to which its products may be put or the conditions of use, it makes no warranties concerning the fitness or suitability of its products for a particular use or purpose. You should thoroughly test any proposed use of our products and independently conclude satisfactory performance in your application. Likewise, if the manner in which our products are used requires governmental approval or clearance, you must obtain it. Shin-Etsu Silicones, Inc. warrants only that its products will meet its specifications. There is no warranty of merchantability of fitness of use, nor any other expressed or implied warranties. The user's exclusive remedy and Shin-Etsu Silicones, Inc.'s sole liability is limited to refund of the price or replacement of any product shown to be otherwise than as warranted. Shin-Etsu Silicones, Inc. will not be liable for incidental or consequential damages of any kind. Suggestions of uses should not be taken as inducements to infringe any patents.