



SV-14001U

Shin-Etsu Silicones of America, Inc.
800-544-1745

Product Description

SV-14001U is designed as an excellent low durometer molding material with low compression set and overall excellent physical properties.

Packaging Information

50lb box or 1000lb gaylord

Typical Properties

Type of HCR	General Purpose
Cure Agent	DBPH Paste (33%)
Durometer	40
Tensile Strength (psi)	1100
Elongation (%)	600
Specific Gravity	1.09
Tear Die B (ppi)	70
Compression Set (%)	10
Comp. Set Time (hours)	22
Comp. Set Temp. (°C)	177
Comp. Set Temp. (°F)	350.6
Press Cure/Post Cure	Press
Cure Time (minutes)	10
Cure Temp. (°C)	177
Cure Temp. (°F)	350.6
Ratio of Catalyst to Material	1.2 : 100

Note: Values are not for specification purposes.

Storage and Shelf Life

Store in a cool, dry place

Warranty- The information and data contained herein are believed to be accurate and reliable; however it is the user's responsibility to determine suitability of use. Since Shin-Etsu Silicones, Inc. cannot know all of the uses to which its products may be put or the conditions of use, it makes no warranties concerning the fitness or suitability of its products for a particular use or purpose. You should thoroughly test any proposed use of our products and independently conclude satisfactory performance in your application. Likewise, if the manner in which our products are used requires governmental approval or clearance, you must obtain it. Shin-Etsu Silicones, Inc. warrants only that its products will meet its specifications. There is no warranty of merchantability of fitness of use, nor any other expressed or implied warranties. The user's exclusive remedy and Shin-Etsu Silicones, Inc.'s sole liability is limited to refund of the price or replacement of any product shown to be otherwise than as warranted. Shin-Etsu Silicones, Inc. will not be liable for incidental or consequential damages of any kind. Suggestions of uses should not be taken as inducements to infringe any patents.