



## X-30-4377U

Shin-Etsu Silicones of America, Inc.  
800-544-1745

### Product Description

X-30-4377U is a 60 durometer high strength and one of a series of easy processing silicone rubber bases. It is used in a variety of applications. X-30-4377U can be molded, extruded, or calendared.

### Product Features

- This product can be blended with other Shin-Etsu general purpose or no post cure bases for intermediate properties. The choice between these bases will depend on specific requirements.

### Typical Properties

Type of HCR	High Strength
Cure Agent	C-25 A/B
Durometer	60
Tensile Strength (psi)	1520
Elongation (%)	600
Specific Gravity	1.16
Tear Die B (ppi)	55
Cure Time (minutes)	10
Cure Temp. (°C)	120
Cure Temp. (°F)	248
Post Cure Time (hours)	4
Post Cure Temp. (°C)	200
Post Cure Temp. (°F)	392

*Note: Values are not for specification purposes.*

### Storage and Shelf Life

Store in a cool, dry place.

Warranty- The information and data contained herein are believed to be accurate and reliable; however it is the user's responsibility to determine suitability of use. Since Shin-Etsu Silicones, Inc. cannot know all of the uses to which its products may be put or the conditions of use, it makes no warranties concerning the fitness or suitability of its products for a particular use or purpose. You should thoroughly test any proposed use of our products and independently conclude satisfactory performance in your application. Likewise, if the manner in which our products are used requires governmental approval or clearance, you must obtain it. Shin-Etsu Silicones, Inc. warrants only that its products will meet its specifications. There is no warranty of merchantability of fitness of use, nor any other expressed or implied warranties. The user's exclusive remedy and Shin-Etsu Silicones, Inc.'s sole liability is limited to refund of the price or replacement of any product shown to be otherwise than as warranted. Shin-Etsu Silicones, Inc. will not be liable for incidental or consequential damages of any kind. Suggestions of uses should not be taken as inducements to infringe any patents.