

### Product Description

Shin-Etsu's G-3W-0-H is a low temperature, silicone lubricating grease that provides excellent lubrication to most types of equipment. G-3W-0-H has high thermo-oxidative stability, high moisture resistance, and a wide usable temperature range.

### Product Features

- High thermo-oxidative stability
- High moisture resistance
- Wide usable temperature range
- Firm consistency/stiffness
- Low-temperature lubrication

### Typical Applications

- Providing lubrication to equipment, especially at low temperatures

### Typical Properties

Type	Grease
One/Two Component	One
Low Molecular Weight Siloxane Stripped?	Y
Color	Grayish White
Density @ 23C (g/cm <sup>3</sup> )	0.99
Penetration (1/10mm)	220
Drop Point (C)	200
% Oil Separation	0.5
% Volatile Content	0.35
Oxidative Stability (kPa)	30
Worked Stability (100,000 Strokes)	400
Low-Temp Torque: Starting (mN/m)	329
Low-Temp Torque: Running (mN/m)	122
Usable Temperature Range (C)	-60 to +180

*Note: Values are not for specification purposes.*

Warranty- The information and data contained herein are believed to be accurate and reliable; however it is the user's responsibility to determine suitability of use. Since Shin-Etsu Silicones, Inc. cannot know all of the uses to which its products may be put or the conditions of use, it makes no warranties concerning the fitness or suitability of its products for a particular use or purpose. You should thoroughly test any proposed use of our products and independently conclude satisfactory performance in your application. Likewise, if the manner in which our products are used requires governmental approval or clearance, you must obtain it. Shin-Etsu Silicones, Inc. warrants only that its products will meet its specifications. There is no warranty of merchantability of fitness of use, nor any other expressed or implied warranties. The user's exclusive remedy and Shin-Etsu Silicones, Inc.'s sole liability is limited to refund of the price or replacement of any product shown to be otherwise than as warranted. Shin-Etsu Silicones, Inc. will not be liable for incidental or consequential damages of any kind. Suggestions of uses should not be taken as inducements to infringe any patents.