



KE-1061

Shin-Etsu Silicones of America, Inc.
800-544-1745

Product Description

Shin-Etsu's KE-1061 is a single component, heat cure, phenyl-based polysiloxane potting gel that will cure to form a soft, pliable elastomer to protect sensitive electronic components. KE-1061 provides superior vibration resistance and exhibits excellent, unprimed adhesion to metals, plastics, glass, and ceramics.

Product Features

- Superior vibration resistance
- Excellent electrical insulation
- Cold resistance
- Single component
- Heat cure

Typical Applications

- Protecting sensitive electronic components

Typical Properties

Type	Potting Gel
Cure Type	Addition
One/Two Component	One
Cold Storage	Y
Color	Transparent
Density @ 23C (g/cm ³)	0.97
Viscosity (cps)	600.00
Cure Conditions	30min @ 120C
Penetration (1/10mm)	90
Volume Resistivity (TΩ·m)	3.0
Dielectric Strength (kV/mm)	14
Dielectric Constant	3.0 @ 50Hz
Dielectric Dissipation Factor	5x10 ⁻⁴ @ 50Hz
Thermal Conductivity (W/m·K)	0.20
Usable Temperature Range (C)	-60 to +150

Note: Values are not for specification purposes.

Warranty- The information and data contained herein are believed to be accurate and reliable; however it is the user's responsibility to determine suitability of use. Since Shin-Etsu Silicones, Inc. cannot know all of the uses to which its products may be put or the conditions of use, it makes no warranties concerning the fitness or suitability of its products for a particular use or purpose. You should thoroughly test any proposed use of our products and independently conclude satisfactory performance in your application. Likewise, if the manner in which our products are used requires governmental approval or clearance, you must obtain it. Shin-Etsu Silicones, Inc. warrants only that its products will meet its specifications. There is no warranty of merchantability of fitness of use, nor any other expressed or implied warranties. The user's exclusive remedy and Shin-Etsu Silicones, Inc.'s sole liability is limited to refund of the price or replacement of any product shown to be otherwise than as warranted. Shin-Etsu Silicones, Inc. will not be liable for incidental or consequential damages of any kind. Suggestions of uses should not be taken as inducements to infringe any patents.